

GETREN® R 4880 (biodegradable)

Chemical description

Biodegradable release agent based on organic substances, silicone oil free

Physical properties

Appearance	yellowish, clear
Active substance content	100%
Viscosity at 25°C	1900–2500 mPas
Density (25°C)	approx. 1 g/cm ³

Application

GETREN® R 4880 is a release agent for shaped rubber hoses, mainly used for EPDM and per-oxydic EPDM. It is also suitable for NBR, ECO, AEM, CR, CM, PVC, Silicone as well as VAMAC® and FKM rubber mixtures.

Advantages

- Excellent slide and release properties
- Good lubrication on the mandrel
- No foaming on hot surfaces
- Water soluble, thus easily washable with water, preferably at higher temperatures without addition of surfactants
- 98 % biodegradable (as determined by the Zahn-Wellens-Test OECD 302 B) by DIN EN ISO 9888 within 7 days
- No labelling

Dosage/Handling

GETREN® R 4880 is recommended to be used in non-diluted form. The release agent should be

applied by dipping or brushing of the mandrels. Dilution with water is possible and even required for its washability. However, very strong dilutions during drifting may reduce the release effect, thus all dilutions must be tested first under the customer's specific circumstances. For further information please contact our technical managers.

Registration status

The components of GETREN® R 4880 are listed in the following chemical inventories:
EINECS, TSCA, ENCS, CHINA, ECL

Storage stability

In originally sealed containers and at temperatures between 10 °C and 30 °C GETREN® R4880 can be stored for at least 1 year. Protect from frost!

Packaging

200 kg PE drum (800 kg per pallet)
1 000 kg PE container

Hazardous goods classification

Information concerning

- classification and labelling according to regulations for transport and for dangerous substances
- protective measures for storage and handling
- measures in case of accidents and fire
- toxicity and ecological effects

is given in our material safety data sheets.

07/2015

Trademark notice and legal notice

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

(Status: July 2015)

Evonik Nutrition & Care GmbH

Goldschmidtstr. 100, 45127 Essen, Germany

Phone Europe +49 201 173-2665, Asia +86 21 61191 125, Americas +1 804 727 0700
interface-performance@evonik.com, www.evonik.com/interface-performance