

GETREN® P 3200 N

Chemical description

Mixture of different siloxanes

Physical properties

Appearance	Colourless, clear – slightly turbid
Viscosity (25 °C)	10 – 50 mPas
Specific gravity (25 °C)	approx. 0.95 g/cm ³
Active content	100 %

Application

GETREN® P 3200 N is used as a sliding polymer for the assembly of building and window profiles.

Advantages

- GETREN® P 3200 N provides a dry and stable film on the surface of the profile.
- Migration of the sliding polymer into the rubber does not occur.
- GETREN® P 3200 N forms a hydrophobic protective coating.
- It improves the colour strength of the rubber profile.
- Coated seals that come into contact to acrylic glass (i. E. Plexiglas®) or polycarbonate glass (i. E. Makrolon®) do not cause stress cracks.



Left bar:
visible formation of stress cracks due to incompatible sliding agent

Right bar:
Plexiglas® test without stress cracks with GETREN® P 3200 N

Dosage/Handling

GETREN® P 3200 N is a ready-to-use-product and should not be diluted with water as this might result in stability problems. It should be applied by spraying or dipping after vulcanisation.

Registration status

The components of GETREN® P 3200 N are listed in the following chemical inventories:

EINECS, TSCA, DSL, ENCS, AICS, ECL, PICCS, IECSC (China)

Storage stability

In originally sealed containers GETREN® P 3200 N can be stored for at least 1 year.

Packaging

200 kg PE drum (800 kg per pallet)

Hazardous goods classification

Information concerning

- classification and labelling according to regulations for transport and for dangerous substances
- protective measures for storage and handling
- measures in case of accidents and fire
- toxicity and ecological effects

is given in our material safety data sheets.

07/2015

Trademark notice and legal notice

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

(Status: July 2015)

Evonik Nutrition & Care GmbH

Goldschmidtstr. 100, 45127 Essen, Germany

Phone Europe +49 201 173-2665, Asia +86 21 61191 125, Americas +1 804 727 0700

interface-performance@evonik.com, www.evonik.com/interface-performance